

Description

Resbuild Gripfast is supplied in composite packs, each containing sufficient material to provide a slip-resistant Epoxy coating system for 5 square metres of surface. Resbuild Gripfast is applied in a single coat operation which reduces the curing period of the system prior to trafficking. Apart from the excellent slip resistance characteristics, the coating system has very good abrasion and chemical resistant properties. The slip resistant AGGREGATE consists of graded Aluminium Oxide.

Typical Uses

As a slip resistant protective coating for concrete, metal and wood surfaces.

Advantages

- Solvent free, low odour
- Excellent slip resistance
- Tough and durable
- Easily applied
- Hygienic and easily cleaned
- Good chemical resistance

Typical Properties

Pot life @ 20C: 30 Minutes

Colours: Light Grey, Mid Grey, Red and Green

Tack Free Time @20C: 3 hours

Hard Dry Time @ 20C: 6 hours

Full Chemical Resistance @20C: 7 days

Adhesive strength to Concrete: 3.7MPd.(concrete failure)

Chemical resistance: Excellent resistance to dilute acids and alkalis, oil, petrol, diesel, and inorganic salts.

Mohs Hardness of Aggregate: 9

Packaging

Resbuild Gripfast is supplied in 5 square metre packs

Procedure

Surface Preparation

- a) Concrete shall be a minimum of 21 days old and/or the residual moisture content shall be below 6%. Ensure that the concrete is clean and free from dust, laitance, grease, oil, curing compound, and existing paint finishes etc. Smooth concrete, or concrete with soft laitance, shall be mechanically treated by diamond grinding or grit blasting to provide a clean profiled surface. Should this not be practicable then acid etching, although less preferable, is also an option.
- b) Metal surfaces shall be wire brushed or power disced to remove any rust and loose or flaking material. Grit blasting is recommended, where practical, for optimum performance. Coating application should be carried out immediately after preparation.
- c) Wood surfaces shall be sanded to a smooth finish, and all previous coating removed. Previously untreated wood shall be sealed with a coat of Resbuild WB Primer or Resbuild DPM.

Mixing

Pour the contents of the CURING AGENT tin into the BASE container and thoroughly mix, preferably by mechanical means until a uniform colour and consistency is achieved.

Application

Pour the mixed liquid components into a shallow roller tray. Apply by medium pile roller (not foam), to a measured 5 m². Immediately scatter the AGGREGATE uniformly onto the wet coating and 'back roller' to cover and encapsulate the AGGREGATE.

Note: Although sufficient Aggregate is supplied to allow a full scatter, a lighter scatter may be made as required.

Equipment Cleaning

It is impracticable to clean rollers after use. Clean equipment with Resbuild Toolclean prior to curing of the coating.

Curing

Allow to cure for a minimum of 8 hours @ 20°C prior to light foot traffic access. Curing at lower temperatures will extend this period, whereas curing at higher temperatures will allow faster access

Storage and Shelf Life

Store in dry conditions at temperatures between 10°C and 25°C. Do not expose to freezing conditions.

Resbuild Gripfast has a minimum of 12 months shelf life when stored in original, unopened containers in accordance with manufacturer's instructions.

Coverage

5m² per pack.

Limitations

Do not apply to wet or uncured concrete surfaces.
Do not apply at temperatures of 3°C or less.

Health and Safety

Wear gloves and goggles
Wash off splashes immediately with soap and water
Please refer to Material Safety Data Sheet for additional information

Resbuild Gripfast shall be applied strictly in accordance with the manufacturer's instructions.

For specific advice regarding any aspect of this product, please consult our Technical section

The information provided in this Product Data Sheet is intended for general guidance only and is given in good faith based on Resin Building Products Limited current knowledge and experience. No warranty in respect of fitness for a purpose, or any other liability whatsoever can be inferred from the information contained within this data sheet. Users should determine the suitability of the materials for their particular application and should always refer to the most recent issue of the Product Data Sheet for the product concerned. All materials are supplied in accordance with our standard terms and conditions of sale (available upon request).