

Description

Resbuild Tufscreeed Fast Cure is a three pack Epoxy resin based floor screed designed for application at 4-6mm thickness. Resbuild Tufscreeed Fast Cure comprises a BASE component, a CURING AGENT component and a specially graded AGGREGATE component.

Resbuild Tufscreeed Fast Cure is easy to apply and does not stick to the trowel.

Resbuild Tufscreeed Fast Cure is non-dusting, chemical and abrasion resistant, non-slip in nature and may be rapidly opened to traffic.

Typical Uses

Seamless protective, and decorative, thin section screeds for food factories, dairies, abattoirs, plating shops, hospitals, sugar refineries, breweries, chemical bunds, etc.

Advantages

- Fast Curing
- Highly durable
- Abrasion and impact resistant
- Non-slip
- Easily maintained
- Excellent chemical resistance
- Low odour

Typical Properties

Colour: Light grey (any BS4800 or RAL colour can also be supplied).

Density: 2.1kg/litre.

Volume yield: 11.9 litres per pack.

Coverage: 1.9m²-2.0m² @ 6mm thickness.

Pot Life: 30-35 minutes @ 20°C.

Compressive strength: 78 MPa after 7 days.

Flexural strength: 26 MPa.

Tensile strength: 11.4 MPa.

Taber Abrasion Resistance: 80 mg weight loss per 1,000 cycle test (CS17 abrasive wheels).

Water Absorption: <0.1% by weight after 7 days immersion.

Maximum Service Temperature: 70°C (continuous); 90°C (intermittent).

Chemical resistance: Excellent resistance to a wide range of industrial chemicals. Please consult our Technical Department for specific advice.

Packaging

Resbuild Tufscreeed Fast Cure is supplied in 25kg packs.

Procedure

Surface Preparation

- a) Concrete shall be a minimum of 21 days old and/or the residual moisture content shall be below 6%. The floor shall then be mechanically prepared by shot blasting, mechanical scabbling, or similar, to produce a clean, exposed aggregate finish, free from dust, dirt, oil, grease, laitance and other contaminants.
- b) Old concrete shall be mechanically prepared to remove all contaminants. Defective concrete shall be removed, cutting back to sound substrate.

Mixing

The use of a mechanical, forced action mixer such as a Creteangle, is strongly recommended.

Pour the contents of the Curing Agent container into the Base container and mix thoroughly.

The mixed resins shall be poured into a mixing vessel, (Creteangle bucket or similar), and the Aggregate added steadily whilst the mixer is in motion.

Mix for 2-3 minutes until a uniform material is achieved.

Priming

Apply a coat of Resbuild Tack Primer Fast Cure to the prepared surface at a rate of 3.5 to 7.0 m²/kg (depending upon surface texture).

Within 60 minutes of the primer application, Resbuild Tufscreeed Fast Cure may be applied; i.e. whilst the primer is still 'tacky'.

Application

Lay the material, utilising screeding bars or screed box, ensuring good compaction, and finish with a stainless steel or chemically resistant plastic float.

Sealing

The application of a clear sealer is recommended to reduce tendency towards staining and dirt pick up, and thereby ensure optimum ease of cleaning. Apply 1 or 2 coats of Resbuild Screedseal at a nominal rate of 0.15litres/m² per coat. Please refer to Resbuild Screedseal product data sheet.

Equipment Cleaning

Clean equipment with Resbuild Toolclean prior to curing of the screed.

Curing

Allow to cure for a minimum of 4 hours @ 20°C prior to light foot traffic access and 12 hours @ 20° prior to vehicular trafficking.

5 days cure @ 20°C is recommended prior to exposure to chemicals.

Curing will be slower at lower temperatures.

Storage and Shelf Life

Store in dry conditions at temperatures between 10°C and 25°C. Avoid low temperature storage prior to use of the material. Do not expose to freezing conditions.

Resbuild Tufscreeed has a minimum shelf life of 12 months when stored in original, unopened containers in accordance with manufacturer's instructions.

Coverage

A 25kg pack yields 11.4 litres of material, sufficient for an area of 2.85m² @ 4mm thickness.

Limitations

Do not apply to wet or uncured concrete surfaces.
Do not apply at temperatures of 3°C or less.

Health and Safety

Wear gloves and goggles.
Wash off splashes immediately with soap and water.
Please refer to Material Safety Data Sheet for additional information.

Resbuild Tufscreeed Fast Cure shall be applied strictly in accordance with the manufacturer's instructions.

For specific advice regarding any aspect of this product, please consult our Technical Department.

The information provided in this Product Data Sheet is intended for general guidance only and is given in good faith based on Resin Building Products Limited current knowledge and experience. No warranty in respect of fitness for a purpose, or any other liability whatsoever can be inferred from the information contained within this data sheet. Users should determine the suitability of the materials for their particular application and should always refer to the most recent issue of the Product Data Sheet for the product concerned. All materials are supplied in accordance with our standard terms and conditions of sale (available upon request).